



Corporate & Technical

Rmax Operating, LLC
 13524 Welch Road
 Dallas, Texas 75244-5291

Phone: (972) 387-4500

Fax: (972) 387-4673

Email: rmax@rmax.com

Web: www.rmax.com

12-2011

Nominal Thickness	Thermal R-Value ¹						
	R-Matte Plus-3	Thermasheath-3 and TSP-3	Therमारoo Plus-3	TSX-8500 and TSX-8510	Eco-Max	Durasheath-3	TSA-FA-3
0.5	3.2	---	---	---	---	---	---
0.625	4.0	---	---	---	---	---	---
0.75	5.0	---	---	---	4.3	---	---
1.0	---	6.0	6.0	6.0	5.4	6.0	6.0
1.1	---	6.7	6.7	6.7	5.9	6.6	6.6
1.2	---	7.4	7.4	7.4	6.5	7.2	7.2
1.25	---	7.8	7.8	7.8	6.8	7.6	7.6
1.3	---	8.2	8.2	8.2	7.0	7.9	7.9
1.4	---	8.9	8.9	8.9	7.6	8.5	8.5
1.5	---	9.6	9.6	9.6	8.1	9.1	9.1
1.6	---	10.3	10.3	10.3	8.6	9.8	9.8
1.7	---	11.0	11.0	11.0	9.2	10.5	10.5
1.75	---	11.4	11.4	11.4	9.5	10.9	10.9
1.8	---	11.7	11.7	11.7	9.7	11.3	11.3
1.9	---	12.4	12.4	12.4	10.3	12.0	12.0
2.0	---	13.1	13.1	13.1	10.8	12.7	12.7
2.1	---	13.8	13.8	13.8	11.5	13.5	13.5
2.2	---	14.5	14.5	14.5	12.1	14.3	14.3
2.25	---	14.9	14.9	14.9	12.5	14.8	14.8
2.3	---	15.3	15.3	15.3	12.8	15.1	15.1
2.4	---	16	16	16	13.4	15.9	15.9
2.5	---	16.7	16.7	16.7	14.1	16.7	16.7
2.6	---	17.4	17.4	17.4	14.8	17.5	17.5
2.7	---	18.1	18.1	18.1	15.4	18.2	18.2
2.75	---	18.5	18.5	18.5	15.8	18.6	18.6
2.8	---	18.9	18.9	18.9	16.1	19.0	19.0
2.9	---	19.6	19.6	19.6	16.7	19.7	19.7
3.0	---	20.3	20.3	20.3	17.4	20.5	20.5
3.1	---	21.0	21.0	21.0	---	---	21.2
3.2	---	21.7	21.7	21.7	---	---	21.9
3.25	---	22.1	22.1	22.1	---	---	22.2
3.3	---	22.5	22.5	22.5	---	---	22.5
3.4	---	23.2	23.2	23.2	---	---	23.2
3.5	---	23.9	23.9	23.9	---	---	23.9
3.6	---	24.6	24.6	24.6	---	---	24.6
3.7	---	25.3	25.3	25.3	---	---	25.4
3.75	---	25.7	25.7	25.7	---	---	25.8
3.8	---	26.0	26.0	26.0	---	---	26.1
3.9	---	26.7	26.7	26.7	---	---	26.9
4.0	---	27.4	27.4	27.4	---	---	27.6
4.5	---	31.0	31.0	31.0	---	---	31.3

¹ Thermal values are determined by using ASTM C518 test method at 75°F mean temperature on material conditioned according to PIMA Technical Bulletin No. 101.